



**ZENITH** INDUSTRIAL RUBBER  
PRODUCTS PVT. LTD.  
Quality Rubber Solutions

An ISO 9001:2008 Registered Company  
An ISO 14001:2004 Registered Company

## GOVT.RECOGNISED EXPORT HOUSE

### TECHNICAL SPECIFICATIONS

PRODUCT CODE : **EL S 30000**

QUALITY : ELECTRICAL INSUALTION MATTING AS PER CEI 61111:2009

Clause No.	PROPERTIES	SPECIFICATION	
-	Specific gravity	1.50	
-	Hardness, Shore A	70	
-	Tensile strength, Kg/cm <sup>2</sup>	50 Min.	
-	Elongation at break, %	250 Min.	
-	Color	GREY / BLACK	
-	Surface Finish	FINE RIB / FABRIC FINISH / SMOOTH	
<b>AS PER CEI 61111:2009 ELECTRICAL PROPERTIES</b>			
<b>5.5</b>	<b>MECHANICAL TESTS</b>		
<b>5.5.2</b>	Mechanical Puncture test	Min 70 N	
<b>5.5.3</b>	Slip Resistance	Avg. force higher than 50 N	
<b>5.6.2.2 &amp;</b>	<b>Class</b>	<b>PROOF TEST</b>	<b>WITHSTAND TEST</b>
<b>5.6.2.3</b>	Class -0	5 KV for 3 Minutes	10 KV - No electical puncture
	Class -1	10 KV for 3 Minutes	20 KV - No electical puncture
	Class -2	20 KV for 3 Minutes	30 KV - No electical puncture
	Class -3	30 KV for 3 Minutes	40 KV - No electical puncture
	Class -4	40 KV for 3 Minutes	50 KV - No electical puncture
<b>5.7</b>	<b>AGEING TEST AT 70±2 °C/168 HRS</b>		
	Mechanical Puncture test	Should be Minimum 80% of Original Value	
<b>5.8</b>	<b>THERMAL PROPERTIES</b>		
<b>5.8.1</b>	Flame Retardance	Flame should not propogated within a 50 mm diameter from the centre	
<b>5.8.2</b>	Low Temperature Resistance (4 hr at -25 ± 3°C)		
	a) Visual Inspection	No Cracks	
	b) Voltage Withstand	No Electrical Puncture	
<b>5.9</b>	<b>ACID RESISTANCE ( 32 °Baume [37.26 %] sulphuric acid for 8 hrs at 23 ± 2 ° C )</b>		
	a) Voltage Withstand	No Electrical Puncture	
	b) Puncture Resistance	Should be Minimum 75% of Original Value	
<b>5.1</b>	<b>OIL RESISTANCE - Liquid 102 as per Annexure E (For 24 hrs at 70 ± 2°C)</b>		
	a) Voltage Withstand	No Electrical Puncture	
	b) Puncture Resistance	Should be Minimum 75% of Original Value	



A/2, PAREKH MAHAL, 80 VEER NARIMAN ROAD, CHURCHGATE MUMBAI - 400 020.

Email: [info@zenithrubber.com](mailto:info@zenithrubber.com) Website: [www.zenithrubber.com](http://www.zenithrubber.com)