

**EP 60130 F**  
**PRODUCT CODE – EP 60130 FG**



**TECHNICAL SPECIFICATIONS**

PROPERTIES	TEST METHOD	VALUES	TEST METHOD	VALUES
		FPS UNITS		FPS UNITS
SPECIFIC GRAVITY	DIN 53508	1.30 ± 0.05	ASTM D297	1.30 ± 0.05
HARDNESS	DIN 53505	60 ± 5 Sh A	ASTM D2240	60 ± 5 Sh A
TENSILE STRENGTH ( min )	DIN 53504	711 PSI	ASTM D412	50 kg/cm 2
ELONGATION AT BREAK ( min )	DIN 53504	300%	ASTM D412	300 %
COMPRESSION SET (70°C/24 hrs/25% compression) (max)	DIN 53517	40 %	ASTM D395 METHOD B	40 %
TEAR RESISTANCE ( Angular ) min	DIN 53515	101 Lbs/Inch	ASTM D624	18 Kg/cm
CHANGE IN PROPERTIES AFTER				
HEAT AGEING FOR ( 72 hrs. AT 70 °C )			ASTM D573	
--- HARDNESS (Pts)		+ 5 (Max)		+ 5 (Max)
--- TENSILE STRENGTH (%)		+ 10 /-10		+ 10 /-10
--- ELONGATION AT BREAK (%)		+ 10 /-10		+ 10 /-10
POLYMER CONTENT (EPDM)		100%		100%
CHEMICAL RESISTANCE				
--- OZONE		EXCELLENT	ASTM D 1149	EXCELLENT
--- DILUTE ACIDS AND BASES		EXCELLENT		EXCELLENT
--- CONCENTRATED ACIDS AND BASES		EXCELLENT		EXCELLENT
--- OILS		EXCELLENT		EXCELLENT
--- SOLVENTS		NOT RECOMMENDED		NOT RECOMMENDED
TEMPERATURE RANGE		-25° to + 140° C		-25 ° to + 140° C
COLOR		OFF WHITE		OFF WHITE
FINISH	BOTH SIDE SMOOTH FINISH			

Note: All pictures shown are for illustration purpose only. Actual product may vary due to product enhancement.\*