



# ZENITH INDUSTRIAL RUBBER PRODUCTS PVT. LTD.

Quality Rubber Solutions

GOVT. RECOGNISED EXPORT HOUSE

## TECHNICAL SPECIFICATIONS

QUALITY: PATCHES & STRIPS

CODE: NR 60115

PROPERTIES	TEST METHOD	VALUES	
		FPS UNITS	METRIC UNITS
SPECIFIC GRAVITY	DIN 53508	1.15±0.05	1.15±0.05
HARDNESS	DIN 53505	60 ± 5 Sh A	60 ± 5 Sh A
TENSILE STRENGTH ( min )	DIN 53504	2418 PSI	170 kg/cm <sup>2</sup>
ELONGATION AT BREAK ( min )	DIN 53504	475 %	470 %
ABRASION RESISTANCE ( max )	DIN 53516	120 mm <sup>3</sup>	120 mm <sup>3</sup>
COMPRESSION SET (70°C/24 hrs/25% compression) (max)	DIN 53517	20%	20%
TEAR RESISTANCE ( Angular ) min	DIN 515	252 Lbs/Inch	45 Kg/cm
CHANGE IN PROPERTIES AFTER HEAT AGEING FOR ( 72 hrs. AT 70 °C )			ASTM D573
--- HARDNESS (Pts)		+ 5 (Max)	+ 5 (Max)
--- TENSILE STRENGTH (%)		+ 10 / -25	+ 10 / -25
--- ELONGATION AT BREAK (%)		+ 10 / -25	+ 10 / -25
CHEMICAL RESISTANCE			
--- OZONE		FAIR	ASTM D 1149
--- DILUTE ACIDS AND BASES		NOT RECOMMENDED	NOT RECOMMENDED
--- CONCENTRATED ACIDS AND BASES		NOT RECOMMENDED	NOT RECOMMENDED
--- OILS		NOT RECOMMENDED	NOT RECOMMENDED
--- SOLVENTS		NOT RECOMMENDED	NOT RECOMMENDED
TEMPERATURE RANGE		-40° to + 70°C	-40° to + 70°C
COLOUR		BLACK	BLACK
FARIC		WITH & WITHOUT - EP 100 INSERTION	
BONDING LAYER		CN BLUE BONDING LAYER	



141/144, 14<sup>TH</sup> FLOOR, FREE PRESS HOUSE, FREE PRESS JOURNAL MARG 215, NARIMAN POINT MUMBAI - 400021

Email: [info@zenithrubber.com](mailto:info@zenithrubber.com) Website: [www.zenithrubber.com](http://www.zenithrubber.com)