



ZENITH INDUSTRIAL RUBBER PRODUCTS PVT. LTD.

Quality Rubber Solutions

An ISO 9001:2008 Registered Company
An ISO 14001: 2004 Registered Company

GOVT.RECOGNISED EXPORT HOUSE

TECHNICAL SPECIFICATIONS

QUALITY : NR/ SBR **AMOEBA DESIGN MAT**
CODE: AM 65

PROPERTIES	TEST METHOD	VALUES	TEST METHOD	VALUE
		FPS UNITS		METRIC UNITS
SPECIFIC GRAVITY	DIN 53508	1.45 ±0.05	ASTM D297	1.45 ±0.05
HARDNESS	DIN 53505	65 ± 5 Sh A	ASTM D2240	65 ± 5 Sh A
TENSILE STRENGTH (min)	DIN 53504	711 PSI	ASTM D412	35 kg/cm2
ELONGATION AT BREAK (min)	DIN 53504	250%	ASTM D412	250%
ABRASION RESISTANCE MAX	DIN 53516	300 mm ³		300 mm ³
COMPRESSION SET (70°C/24HRS/25%SET)	DIN ISO 815-1	30 %		30 %
TEAR RESISTANCE (Angular) min	DIN 53515	112 Lbs/Inch	ASTM D624	20 Kg/cm
CHANGE IN PROPERTIES				
HEAT AGEING (72 hrs. AT 70°C)			ASTM D573	
--- HARDNESS (Pts)		+ 5 (Max)		+ 5 (Max)
--- TENSILE STRENGTH (%)		+ 20 / - 20		+ 20 / - 20
--- ELONGATION AT BREAK (%)		+ 25 / - 25		+ 25 / - 25
VOLUME SWELLING AT 70 °C FOR 72 HRS IN			ASTM D 571	
IRM OIL NO. 1		NOT RECOMMENDED		NOT RECOMMENDED
IRM OIL NO 2		NOT RECOMMENDED		NOT RECOMMENDED
IRM OIL NO,3		NOT RECOMMENDED		NOT RECOMMENDED
CHEMICAL RESISTANCE				
--- OZONE		NOT RECOMMENDED	ASTM D 1149	NOT RECOMMENDED
--- DILUTE ACIDS AND BASES		FAIR		FAIR
--- CONCENTRATED ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
--- OILS		NOT RECOMMENDED		NOT RECOMMENDED
--- SOLVENTS		NOT RECOMMENDED		NOT RECOMMENDED
TEMPERATURE RANGE		-30° to + 70° C		-30° to + 70° C
COLOUR		BLACK		BLACK
MAT DESIGN	AMOEBA DESIGN MAT			



A/2, PAREKH MAHAL, 80 VEER NARIMAN ROAD, CHURCHGATE MUMBAI - 400 020.

Email: info@zenithrubber.com

Website: www.zenithrubber.com