



# ZENITH INDUSTRIAL RUBBER PRODUCTS PVT. LTD.

Quality Rubber Solutions

An ISO 9001:2008 Certified Company  
An ISO 14001:2004 Certified Company

GOVT.RECOGNISED EXPORT HOUSE

## TECHNICAL SPECIFICATIONS

### QUALITY : NATURAL RUBBER (ABRASION RESISTANT SHEET) CODE: PL 45110

PROPERTIES	TEST METHOD	VALUES	
		FPS UNITS	METRIC UNITS
SPECIFIC GRAVITY	DIN 53508	1.10±0.05	1.10±0.05
HARDNESS	DIN 53505	45 ± 5 Sh A	45 ± 5 Sh A
TENSILE STRENGTH ( min )	DIN 53504	2137 PSI	150 kg/cm2
ELONGATION AT BREAK ( min )	DIN 53504	600%	600%
ABRASION RESISTANCE ( max )	DIN 53516	150 mm3	150 mm3
COMPRESSION SET (70°C/24 hrs/25% compression) (max)	DIN 53517	30%	30%
TEAR RESISTANCE ( Angular ) min	DIN 53515	168 Lbs/Inch	30 Kg/cm
CHANGE IN PROPERTIES AFTER HEAT AGEING FOR ( 72 hrs. AT 70 °C )			ASTM D573
--- HARDNESS (Pts)		+ 5 (Max)	+ 5 (Max)
--- TENSILE STRENGTH (%)		+ 10 / -25	+ 10 / -25
--- ELONGATION AT BREAK (%)		+ 10 / -25	+ 10 / -25
VOLUME SWELL : AT 70°C FOR 72 HRS			ASTM D 471
IN IRM OIL NO.1		NOT RECOMMENDED	NOT RECOMMENDED
IN IRM OIL NO.2		NOT RECOMMENDED	NOT RECOMMENDED
IN IRM OIL NO.3		NOT RECOMMENDED	NOT RECOMMENDED
<b>CHEMICAL RESISTANCE</b>			
--- OZONE		FAIR	ASTM D 1149
--- DILUTE ACIDS AND BASES		FAIR	FAIR
--- CONCENTRATED ACIDS AND BASES		NOT RECOMMENDED	NOT RECOMMENDED
--- OILS		NOT RECOMMENDED	NOT RECOMMENDED
--- SOLVENTS		NOT RECOMMENDED	NOT RECOMMENDED
TEMPERATURE RANGE		-30 ° to + 70° C	-30 ° to + 70° C
COLOUR & DESIGN		RED WITH GREY NEOPRENE BONDING LAYER & DIAMOND DESIGN	RED WITH GREY NEOPRENE BONDING LAYER & DIAMOND DESIGN



141/144,14<sup>TH</sup> FLOOR, FREE PRESS HOUSE, FREE PRESS JOURNAL MARG 215,NARIMAN POINT MUMBAI -

Email: [info@zenithrubber.com](mailto:info@zenithrubber.com) Website: [www.zenithrubber.com](http://www.zenithrubber.com)